

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 July 2005 (21.07.2005)

PCT

(10) International Publication Number
WO 2005/065996 A1

(51) International Patent Classification⁷: **B60R 13/08**,
G10K 11/162, F02B 77/13

(21) International Application Number:
PCT/US2004/042516

(22) International Filing Date:
17 December 2004 (17.12.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/749,084 30 December 2003 (30.12.2003) US

(71) Applicant (for all designated States except US): **OWENS CORNING** [US/US]; One Owens Corning Parkway, Toledo, OH 43659 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **TILTON, Jeffrey, A.** [US/US]; 7904 Sutherland Farm Road, Prospect, KY 40059 (US). **ROCKWELL, Anthony, L.** [US/US]; 5365 Blacklick Eastern Road, Pickerington, OH 43147 (US).

(74) Agents: **GASAWAY, Maria, C.** et al.; Owens Corning Science & Technology Center, 2790 Columbus Road, Bldg 11-7, Granville, OH 43023-1200 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: MULTIDENSITY LINER/INSULATOR FORMED FROM MULTIDIMENSIONAL PIECES OF POLYMER FIBER BLANKET INSULATION



(57) Abstract: In accordance with the purposes of the present invention as described herein, an improved acoustical, compressible, polymer fiber blanket (10) of enhanced performance characteristics is provided. The polymer fiber blanket of the present invention is constructed of a plurality of individual pieces of polymer fiber blanket (12) that have been bonded together via heat and pressure.

WO 2005/065996 A1

MULTIDENSITY LINER/ INSULATOR FORMED FROM MULTIDIMENSIONAL
PIECES OF POLYMER FIBER BLANKET INSULATION

TECHNICAL FIELD AND INDUSTRIAL APPLICABILITY OF THE INVENTION

5 The present invention relates generally to a multilayer acoustical and thermal
liner/insulator formed from multidimensional pieces of a polymeric material, which may
be utilized to insulate an environment such as a passenger compartment of a vehicle from
the heat and sound generated by mechanical components of that vehicle during its
operation. The material is especially useful in automotive undercarpet products or in
10 applications where compression recovery is an important property. Other uses include
application in insulating appliances such as dishwashers and clothes dryers and providing
sound and thermal insulation for furnaces, air conditioning units and ductwork in
buildings including homes, offices and industrial structures.

15 BACKGROUND OF THE INVENTION

Acoustical insulation is well known in the art. Acoustical insulation typically
relies upon both sound absorption, that is the ability to absorb incident sound waves, and
transmission loss, that is the ability to reflect incident sound waves, in order to provide
sound attenuation. One of the more prevalent uses of such insulation is in the motorized
20 vehicle field where engine compartments, fire walls, fender wells, doors, floor pans and
other components of the passenger compartment shell are commonly acoustically
insulated to reduce engine and road noise for the benefit and comfort of passengers.

In the automotive undercarpet industry, it is important to prevent compression of
the carpet surrounding the area on which a load, that is, a passenger's feet, is placed. By
25 preventing compression, acoustical and insulative properties to be maintained. Various
methods of manufacturing or fabricating acoustical and thermal insulators are known in
the art. Typically, an automotive carpet is placed over a cotton shoddy or a uniform
polymer based mat. These undercarpets are typically produced by carding, garnetting or
air laid systems known in the art. Examples of other methods and products are found in
30 U.S. 5,266,374, and U.S. publication nos. 2003/0066708 A1 and 2003/0096079.

U.S. 5,266,374 teaches a carpet for vehicles that prevents the transmission of
sound and vibration into a vehicle cabin. '374 teaches a rigid polyurethane sheet laid on a
metal panel, such as that of a vehicle floor. The polyurethane sheet comprises an

elastomeric rubber layer, which further comprises a plurality of incompressible, square blocks which are intermittently disposed between the rigid and elastomeric layers. The rigid blocks are arranged so as to not come into contact with one another.

U.S. Pub. No. 2003/0096079 A1 teach a sound attenuating laminate for use in vehicles including a substrate having opposite first and second surfaces formed of foam, massback, thermoformable fibrous material. A first surface is attached to a vehicle panel. A non-porous polyurethane layer is applied to either portions of or the entire substrate second surface. The laminate is formed by forming the substrate in the shape of the article to which it is to be applied and then spraying the polyurethane layer onto the substrate.

U.S. Pub. No. 2003/0066708 A1 teach a sound attenuating composite article for vehicles having several layers of material. The first layer is either fiber batting or acoustic foam, the second layer is a thermoplastic material fused to the surface of the first layer, the third layer is a thermoplastic material fused to the surface of the second layer, and the fourth layer is a woven or nonwoven mixture of fibers attached to the third layer of material. The article is formed by providing the first layer and then extruding a second layer of thermoplastic material onto the first layer, compressing the first and second layers and then extruding a third layer of thermoplastic material onto the second layer. Scrim material is then attached to the third layer of thermoplastic material and then all four layers are compressed via nip rolls. Finally, the article is place in a heated mold and heated via infrared radiation.

In many acoustical insulation applications and particularly those relating to motorized vehicles, high compressive strength is advantageous, especially in vehicle carpet applications so that the acoustical properties are maintained. As demonstrated by these prior art patents, it has generally been found necessary to coat a uniform substrate with one or more layers of thermoplastic material. A need is therefore identified for an improved insulation providing enhanced acoustical properties while also exhibiting compression-recovery. There is also a need for a product that can be manufactured at a lower cost and reduces waste.

SUMMARY OF THE INVENTION

In accordance with the purposes of the present invention as described herein, an improved acoustical, compressible, polymer fiber blanket of enhanced performance characteristics is provided. The polymer fiber blanket of the present invention is

constructed of a plurality of individual pieces of polymer fiber blanket that have been bonded together via heat and pressure. The blanket is manufactured by cutting pieces of polymer fiber blanket from a uniform sheet of material that can be either pre-consumer or post-consumer material. The pre-cut, uniform sheet is made of staple fibers, that is, glass
5 fibers and bicomponent thermoplastic fibers such as polyester with copolyester bicomponent fibers. Other polymers that may be used as thermoplastic fibers include polypropylene, polyethylene and nylon. After pieces of the uniform sheet are cut, they are laid down in a randomly oriented pattern. The individual pieces of polymer fiber blanket are then bonded by heat and pressure to form a polymer fiber blanket having enhanced
10 compressive qualities. In the formation of the blanket, the individual pieces build thickness easily and allow lower density products to be produced for a given thickness without sacrificing compressive recovery properties.

The individual pieces of the polymer fiber blanket are cut from a uniform sheet which includes a pad of fibrous material having a lofty, acoustically insulating portion.

15 The individual pieces may be cut from a pre-made sheet of fibrous material or may be cut from scrap material. The polymer fiber blanket also includes a relatively higher density skin along at least one face thereof.

The pad is a nonlaminated and, accordingly, the potential for the relatively higher density skin to delaminate from the remainder of the pad is eliminated. In one
20 embodiment of the invention, the pad includes a higher density skin along a second face thereof as well.

In another embodiment of the present invention, the polymer fiber blanket may be bonded to at least one uniform layer of flexible, polymeric fibrous material, such as the uniform sheet from which individual pieces of polymer fiber blanket are cut from, as
25 described above.

Still other objects of the present invention will become apparent to those skilled in this art from the following description wherein there is shown and described preferred embodiments of this invention, simply by way of illustration of several of the modes best suited to carry out the invention. As it will be realized, the invention is capable of other
30 different embodiments and its several details are capable of modification in various, obvious aspects all without departing from the invention. Accordingly, the drawings and descriptions will be regarded as illustrative in nature and not as restrictive.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings incorporated in and forming a part of the specification, illustrates several aspects of the present invention and together with the description serves to explain the principles of the invention. In the drawings:

5 Fig. 1 is a perspective view of the polymer fiber blanket of the present invention.

Fig. 2 is a perspective view of another embodiment of the present invention.

Fig. 3 is an end elevational view of the embodiment of the present invention as depicted in Fig. 2.

10 Fig. 4 is an end elevational view of the embodiment of the present invention as depicted in Fig. 1.

Fig. 5 is an end elevation view of uniform blanket used to make the present invention as depicted in Figs. 1-4.

Fig. 6 shows two graphs of compression and recoverability data of the present invention.

15 Fig. 7 is a plan view of a preferred embodiment of the present invention.

Fig. 8 is an perspective view of a cutting device used in accordance with the present invention.

Reference will now be made in detail to the present preferred embodiments of the invention, examples of which are illustrated in the accompanying drawing.

20

DETAILED DESCRIPTION AND PREFERRED EMBODIMENTS OF THE INVENTION

Reference is now made to Fig. 1, which illustrates a first embodiment of the compressible, flexible polymer fiber blanket designated by reference numeral 10. The
25 polymer fiber blanket 10 is constructed of a plurality of individual pieces of polymer fiber blanket 12 that have been bonded together by applying heat and pressure. Fig. 4 is an end elevational view of the product 10 as disclosed in Fig. 1 showing the bonded individual pieces 32.

The individual pieces 12 are produced from a thermally bonded polymer blanket
30 product that is typically made of a combination of staple fibers and bicomponent fibers. The fibrous material may take the form of (a) thermoplastic polymer staple fibers and thermoplastic bicomponent fibers, (b) glass staple fibers and thermoplastic bicomponent fibers and (c) a combination of (a) and (b). The thermoplastic staple fibers and

bicomponent fibers may be selected from a group of materials including but not limited to polyester, polyethylene, polypropylene, nylon and any mixtures thereof. The glass fibers may include E-glass, S-glass or basalt fibers. Natural fibers (for example hemp, kenaf) may also be included.

5 Fig. 5 depicts a uniform, polymer blanket 16 from which the individual pieces 12 (Fig. 1) are cut. The uniform blanket 16 includes a lofty, acoustically insulating portion 18 having a density of between substantially $8.0 - 80.0 \text{ kg/m}^3$ and a relatively higher density skin 20 along one face thereof. The skin 16 has a thickness of between substantially $0.25 - 10.0 \text{ mm}$ and a density of between substantially $32.0 - 800.0 \text{ kg/m}^3$.

10 The density of the skin 20 may be substantially constant throughout its thickness or it may vary gradually lower from a maximum density along the outer face thereof to a density just above that of the insulating portion 18 along the inner portion thereof. Where the density of the skin 20 varies, the average density for the skin falls within the indicated range.

15 The uniform blanket 16 may not contain the skin 20 or, in the alternative, may contain a first skin 20 and a secondary skin (not shown). Further, the blanket may include a facing, on one or both sides, to improve strength and/or surface appearance. Other embodiments and details of the material that may be used with the present invention are discussed in U.S. patent no. 6,669,265 issued December 30, 2003.

20 The blanket 10 is made by cutting pieces of polymer fiber blanket from a uniform sheet of material that can be either pre-consumer or post-consumer, that is, scrap material. A pre-cut, uniform sheet is made of staple fibers, that is, glass fibers and bicomponent thermoplastic fibers, as described above. The uniform sheet is cut into a plurality of individual pieces, preferably geometric shapes, that is, cubes. The uniform sheet may be
25 cut by any means known in the art. A preferable way of cutting the uniform sheet is shown in Fig. 8. Fig. 8 shows uniform sheet 70 being drawn in between splitter unit 72, having multiple blades, and guide roller 71. Splitter unit 72 divides the sheet 70 into strips of material 73. The strips of material 73 are then fed in between cutting roller 74, having multiple blades, and guide roller 77 where the strips of material 73 are cut into individual
30 pieces 76 by cutting roller 74. After the cutting process, the individual pieces of blanket are then laid down onto a forming chain and then bonded by heat and pressure.

As the pieces of blanket are compressed, they become randomly oriented as depicted in Fig. 1. While being subjected to heat and pressure, the bicomponent fibers

from which the pieces of blanket are made as described above, are activated causing the fibers in the individual pieces to bond together forming a uniform blanket.

As a result of the random orientation of the pieces 12 in the blanket 10, as shown in Fig. 1, the blanket 10 exhibits increased compressive resistance over a uniform blanket.

As such, the blanket 10 is suitable for use in automotive undercarpet products or other applications where compressive resistance is important such as cushioning for seating. To better control compression of the polymer blanket, the individual pieces 12 may be arranged in a controlled pattern instead of a random orientation. Any pattern may be implemented; Fig. 7 shows a sample of such a pattern, showing individual pieces 34 are arranged in a controlled pattern on uniform blanket 36.

Fig. 6 shows compression and recovery data of the present invention as compared to a uniform blanket. Graph 1 shows percent recovery (wet and dry) of a 68 gsf uniform blanket compared to a 1" (2.54 cm) 60 gsf cube and a 1" 45 gsf cube of the present invention. Graph 2 shows percent compression (wet and dry) of a 68 gsf uniform blanket compared to a 1" 60 gsf cube and a 1" 45 gsf cube of the present invention. The test method used is SAE J1352 "Compression and Recovery Method BC". As shown in Fig. 6, the cubed product of the present invention provides improved wet recovery and improved wet and dry compression over the uniform blanket.

Although Fig. 1 depicts the individual pieces 12 in the blanket 10 as being the same shape, for example, square, other geometric shapes may be cut. The geometric shapes can be configured in the cutting process to optimize compressive recovery results. The pieces may be a variety of shapes, that is, triangular, square, etc. or may be the same shape. The geometric shapes can be configured in the cutting process to optimize compressive recovery results. It is not critical that the pieces that make up the blanket have the same shape or be composed of the same fibrous material so long as the pieces can be bonded together. In certain instances, it may be desirable to alter the geometry of the pieces or fiber content to "tune" the desired physical properties. The size of the individual pieces 12 may vary according to the use of the blanket. Typical sizes of the individual pieces range from about 0.5 to about 1.25 square inches (about 3.23 to about 8.06 square cm).

Fig. 2 illustrates a second embodiment of the present invention. Blanket 22 is depicted as having individual pieces of polymer fiber blanket 24 bonded to a uniform polymer blanket 26. Fig. 3 is an end elevational view of the product 22 as disclosed in

Fig. 2 showing the individual pieces 30 bonded to the uniform polymer blanket 28.

Both the individual pieces 24 and the uniform polymer blanket 26 are described above in detail. The blanket 22 is made by applying individual pieces of polymer fiber blanket 24 on top of a uniform polymer blanket 26. Both the individual pieces 24 and the
5 uniform polymer blanket 26 are then bonded by heat and pressure.

The use of the uniform polymer blanket 26 in combination with the individual pieces 24 provides greater strength to the product. There are several advantages to using the uniform blanket in combination with individual pieces, that is, the uniform blanket provides a smooth surface for bonding that is, bonding to an automotive floor surface.
10 Further, by adding or omitting individual pieces, the properties of the product may be changes, that is, creating a softer or stiffer product. The acoustics may also be tuned by adding or omitting pieces on the uniform blanket.

In applications requiring superior heat insulative characteristics, a facing layer 21 or 23, as shown in Fig. 5, may be formed from a heat reflective material such as a metallic
15 foil (for example aluminum or other heat reflective metal). The facing layer may be applied the uniform polymer blanket 16 (Fig. 5) and/or the individual pieces 12 (Fig. 1) may be cut from and uniform polymer blanket having a facing layer 21 or 23. Where a metallic foil is used foil thickness is generally in the range of 0.025 – 0.25 mm. The thickness selected is based upon the temperature, durability and structural requirements of
20 the particular product application.

The facing layer 21 or 23 may be reinforced or non-reinforced. Reinforcements are included to add durability and structural integrity. Reinforcements may take the form of fibrous scrims, fibrous mats or fibrous webs. For many applications, the reinforcement is made from a relatively strong fiber such as fiberglass. The strands may be materials
25 other than glass which provide the desired properties (for example polyester).

Alternative reinforcement materials for the facing layer 21, 23 include but are not limited to glass mats, polymer mats and blended mats. The reinforcement may be pre-attached to the metallic foil. Alternatively loose laid reinforcement may be utilized. In most applications, the foil layer reinforcement provides improved tear resistance, strength
30 and/or acoustical insulating properties. However, in many applications, it should be appreciated that no reinforcement is necessary.

The facing layer 21 or 23 (reinforced or non-reinforced) is attached to the polymer based pad 18 by means of a heat activated adhesive. The adhesive utilized may be a

thermoplastic sheet or thermoplastic web material that tends to melt and flow at temperatures between 200°F-350° F (93.3°C-176.6°C). Adhesives of this type are desirable because they can be activated during the molding phase of production. Besides thermoplastic sheets and webs, adhesives such as hot melts, latex and various heat-activated resins may be utilized. The adhesive may be a separate layer as illustrated or the adhesive may already be attached to the facing layer 21 or 23.

Other embodiments of the present invention (not shown) may be utilized. For example, the embodiment as disclosed in Fig. 2, may have a double layer of uniform polymer blanket 26. In another alternative, the polymer blanket 10 may comprise a double layer of individual pieces 12. A water barrier may also be incorporated such as that disclosed in U.S. patent no. 6,669,265 issued December 30, 2003.

The foregoing description of preferred embodiments of the invention has been presented for purposes of illustration and description. It is not intended to be exhaustive or to limit the invention to the precise form disclosed. Obvious modifications or variations are possible in light of the above teachings.

The embodiments were chosen and described to provide the best illustration of the principles of the invention and its practical application to thereby enable one of ordinary skill in the art to utilize the invention in various embodiments and with various modifications as are suited to the particular use contemplated. All such modifications and variations are within the scope of the invention as determined by the appended claims when interpreted in accordance with the breadth to which they are fairly, legally and equitably entitled.

WHAT IS CLAIMED IS:

1. A compressible, flexible, polymer fiber blanket (10) comprising a plurality of individual pieces of polymer fiber blanket (12) bonded together, wherein said plurality of individual pieces of polymer fiber blanket are produced from a thermally bonded polymer blanket product.
2. The compressible, flexible, polymer fiber blanket of claim 1, wherein said thermally bonded polymer blanket product comprises staple fibers and bicomponent fibers.
3. The compressible, flexible, polymer fiber blanket of claim 2, staple fibers comprise glass fibers and said bicomponent fibers comprise thermoplastic fibers.
4. The compressible, flexible, polymer fiber blanket of claim 1, wherein said individual pieces of polymer fiber blanket are made of scrap polymer fiber blanket.
5. The compressible, flexible, polymer fiber blanket of claim 1, wherein said individual pieces of polymer fiber blanket are randomly oriented.
6. The compressible, flexible polymer fiber blanket of claim 1, wherein said individual pieces of polymer fiber blanket are arranged in a controlled pattern.
7. The compressible, flexible polymer fiber blanket of claim 1, wherein said individual pieces of polymer fiber blanket are geometric in shape.
8. The compressible, flexible polymer fiber blanket of claim 1, wherein said individual pieces of polymer fiber blanket comprise a lofty, acoustically insulating portion having a density of between substantially $8.0 - 80.0 \text{ kg/m}^3$ and a relatively higher density skin along at least one face thereof, said skin having a thickness of between substantially $0.25 - 10.0 \text{ mm}$ and a density of between substantially $32.0 - 80.0 \text{ kg/m}^3$.
9. The compressible, flexible polymer fiber blanket of claim 1, wherein said blanket is an automotive undercarpet.
10. The compressible, flexible polymer fiber blanket of claim 1, wherein said blanket is a nonlaminated.
11. The compressible, flexible polymer fiber blanket of claim 1, wherein said polymer fiber blanket has a percent wet compression of between about 15 to about 18 percent.
12. The compressible, flexible polymer fiber blanket of claim 1, wherein said polymer fiber blanket has a percent dry compression of between about 16 to about 21 percent.

13. The compressible, flexible polymer fiber blanket of claim 1, wherein said polymer fiber blanket has a percent dry wet recovery of between about 85 to about 87.5 percent.

14. The compressible, flexible polymer fiber blanket of claim 1, wherein said polymer blanket is thermally bonded to at least one uniform layer of flexible, polymeric fibrous material.

15. The compressible, flexible polymer fiber blanket of claim 13 further comprising a second polymer blanket comprising a plurality of individual pieces of polymer fiber blanket bonded together in a pattern, wherein said plurality of individual pieces of polymer fiber blanket are produced from a thermally bonded polymer blanket product; wherein said second polymer blanket is positioned between said uniform layer of flexible, polymeric fibrous material and said compressible, flexible polymer fiber blanket.

16. The compressible, flexible polymer fiber blanket of claim 13, wherein said polymeric fibrous material has a lofty, acoustically insulating portion having a density of between substantially $8.0 - 80.0 \text{ kg/m}^3$ and a relatively higher density skin along a first face thereof, said skin having a thickness of between substantially $0.25 - 10.0 \text{ mm}$ and a density of between substantially $32.0 - 800.0 \text{ kg/m}^3$, said fibrous material being selected from a group consisting of (a) thermoplastic polymer staple fibers and thermoplastic bicomponent fibers, (b) glass staple fibers and thermoplastic bicomponent fibers and (c) a combination of (a) and (b).

17. The compressible, flexible polymer fiber blanket of claim 14, wherein said fibrous material is selected from a group of materials consisting of polyester, polyethylene, polypropylene, nylon, glass fibers, natural fibers and any mixtures thereof.

18. The compressible, flexible polymer fiber blanket of claim 14, wherein said polymeric fibrous material includes said relatively higher density skin along a second face thereof.

19. The compressible, flexible polymer fiber blanket of claim 1, wherein said blanket further comprises at least one facing layer.

20. The compressible, flexible polymer fiber blanket of claim 17, wherein said facing layer comprises metallic foil, glass mats, polymer mats and blends thereof.

21. The compressible, flexible polymer fiber blanket of claim 1, wherein said blanket further comprises at least one water barrier layer.

22. A method of producing a compressible, flexible polymer fiber blanket (10)

comprising the steps of:

- a) providing a plurality of individual pieces of polymer fiber blanket (12);
- b) laying said plurality of pieces of polymer fiber blanket in a randomly oriented pattern;
- c) applying sufficient heat and pressure to said plurality of individual pieces of polymer fiber blanket to form said compressible, flexible polymer fiber blanket.

23. The method of claim 22, wherein said individual pieces of polymer fiber blanket are made of scrap polymer fiber blanket.

24. The method of claim 22, wherein said individual pieces of polymer fiber blanket are geometric in shape.

25. The method of claim 22, wherein said individual pieces of polymer fiber blanket comprise a lofty, acoustically insulating portion having a density of between substantially $8.0 - 80.0 \text{ kg/m}^3$ and a relatively higher density skin along at least one face thereof, said skin having a thickness of between substantially $0.25 - 10.0 \text{ mm}$ and a density of between substantially $32.0 - 800.0 \text{ kg/m}^3$.

26. The method of claim 22, wherein said blanket is an automotive undercarpet.

27. The method of claim 22, wherein said pad is a nonlaminated.

28. The method of claim 22, wherein said polymer fiber blanket has a percent wet compression of between about 15 to about 18 percent.

29. The method of claim 22, wherein said polymer fiber blanket has a percent dry compression of between about 16 to about 21 percent.

30. The method of claim 22, wherein said polymer fiber blanket has a percent dry wet recovery of between about 85 to about 87.5 percent.

31. The method of claim 22, wherein said polymer blanket is thermally bonded to at least one layer of flexible, polymeric fibrous material.

32. The method of claim 26, wherein said polymeric fibrous material has a lofty, acoustically insulating portion having a density of between substantially $8.0 - 80.0 \text{ kg/m}^3$ and a relatively higher density skin along a first face thereof, said skin having a thickness of between substantially $0.25 - 10.0 \text{ mm}$ and a density of between substantially $32.0 - 800.0 \text{ kg/m}^3$, said fibrous material being selected from a group consisting of (a) thermoplastic polymer staple fibers and thermoplastic bicomponent fibers, (b) glass staple fibers and thermoplastic bicomponent fibers and (c) a combination of (a) and (b).

33. The method of claim 31, wherein said fibrous material is selected from a group of materials consisting of polyester, polyethylene, polypropylene, nylon, glass fibers, natural fibers and any mixtures thereof.

34. The method of claim 31, wherein said polymeric fibrous material includes said relatively higher density skin along a second face thereof.

35. The method of claim 22, wherein said blanket further comprises at least one water barrier layer.

36. A compressible, flexible, polymer fiber blanket comprising a plurality of individual pieces of polymer fiber blanket thermally bonded together wherein said individual pieces of polymer fiber blanket comprise fibrous material having a lofty, acoustically insulating portion having a density of between substantially $8.0 - 80.0 \text{ kg/m}^3$ and a relatively higher density skin along a first face thereof, said skin having a thickness of between substantially $0.25 - 10.0 \text{ mm}$ and a density of between substantially $32.0 - 800.0 \text{ kg/m}^3$, said fibrous material being selected from a group consisting of (a) thermoplastic polymer staple fibers and thermoplastic bicomponent fibers, (b) glass staple fibers and thermoplastic bicomponent fibers and (c) a combination of (a) and (b).

FIG. 1




FIG. 2




FIG. 3




FIG. 4







FIG. 5





Product	Dry Recovery	Dry Compression	Wet Recovery	Wet Compression
68 gsf Uniform Blanket	97.5	24.1	80.4	22.3
1" cube 60 gsf	96.5	16.3	87.4	17.9
1" cube 45 gsf	96.5	21.3	87.4	17.9

FIG. 6

FIG. 8





FIG. 7



INTERNATIONAL SEARCH REPORT

International Application No

PCT/US2004/042516

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B60R13/08 G10K11/162 F02B77/13

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B60R G10K F02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2003/003835 A1 (TILTON JEFFREY A ET AL) 2 January 2003 (2003-01-02) abstract; figure 1 paragraphs '0016! - '0019!	1, 22, 36
A	DE 39 25 354 A1 (SCHOENBERGER, HELMUT, 8359 SCHOELLNACH, DE) 7 February 1991 (1991-02-07) claims; figures	1, 22, 36
A	DE 44 19 886 A1 (HEINRICH CRONAU GMBH, 66538 NEUNKIRCHEN, DE) 14 December 1995 (1995-12-14) abstract; figures column 2, line 22 - line 54	1, 22, 36

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance, the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance, the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

24 June 2005

Date of mailing of the international search report

04/07/2005

Name and mailing address of the ISA

European Patent Office, P B 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 340-2040, Tx 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

D'Sylva, C

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US2004/042516

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2003003835	A1	02-01-2003	US 6572723 B1 03-06-2003
			BR 0209573 A 13-07-2004
			CA 2444641 A1 12-12-2002
			EP 1392547 A1 03-03-2004
			JP 2004530925 T 07-10-2004
			MX PA03010863 A 17-02-2004
			WO 02098707 A1 12-12-2002
			AU 7138501 A 14-01-2002
			EP 1294558 A2 26-03-2003
			JP 2004501803 T 22-01-2004
			WO 0202302 A2 10-01-2002
			US 2003008581 A1 09-01-2003
DE 3925354	A1	07-02-1991	NONE
DE 4419886	A1	14-12-1995	NONE

THIS PAGE BLANK (USPTO)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)